

Cane Sugar Liquors	A	A	A	A	A	A	A	A	A	A
Carbamate	D	D	B	B	C	B	B	*	A	A
Carbitol	B	B	B	B	B	B	B	B	B	B
Carbolic Acid (Phenol)	D	D	B	B	D	C	D	D	A	A
Carbon Bisulfide	D	D	D	D	C	D	D	D	A	A
Carbon Dioxide	B	B	B	B	A	B	B	B	A	A
Carbonic Acid	A	B	A	A	B	A	A	A	A	A
Carbon Monoxide	B	B	A	A	A	B	B	A	A	A
Carbon Tetrachloride	D	D	D	D	C	D	D	D	A	A
Castor Oil	A	A	B	B	A	A	B	A	A	A

A - Recommended B - Minor to Moderate Effect C - Moderate to Severe Effect D - Not Recommended* Insufficient Data

Chemical	Natural Rubber, Isoprene (NR, IR)	Styrene, Butadiene (SBR, BR)	Butyl (IIR)	EPDM, EPM	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Silicone (SI, VMQ)	Viton, Fluoroelastomer (FKM)	Viton B Fluoroelastomer (FKM)
Cellosolve	D	D	B	B	D	D	D	D	C	D
Cellosolve Acetate	D	D	B	B	D	D	D	D	D	D
Cellulube (Fryquel)	D	D	A	A	D	D	D	A	A	A
China Wood Oil (Tung Oil)	D	D	C	C	A	B	C	D	A	A
Chlorine (Dry)	D	D	D	D	D	C	B	D	A	A
Chlorine (Wet)	D	D	C	C	D	C	C	D	B	A
Chlorine Dioxide	D	D	C	C	D	D	C	*	A	A
Chlorine Trifluoride	D	D	D	D	D	D	D	D	D	D
Chloroacetic Acid	D	D	B	A	D	D	A	*	D	C
Chloroacetone	D	D	B	A	D	C	C	D	D	C
Cholorobenzene	D	D	D	D	D	D	D	D	A	A
Chlorobromomethane	D	D	B	B	D	D	D	D	A	A
Chlorobutadiene	D	D	D	D	D	D	D	D	A	A
Chlorododecane	D	D	D	D	D	D	D	D	A	A
Chloroform	D	D	D	D	D	D	D	D	A	A
O-Chloronapthalene	D	D	D	D	D	D	D	D	A	A
1-Chloro-1-Nitro Ethane	D	D	D	D	D	D	D	D	D	D
Chlorosulfonic Acid	D	D	D	D	D	D	D	D	D	D
Chlorotoluene	D	D	D	D	D	D	D	D	A	A
Chlorox (Sodium Hypochlorite NaOCl)	D	D	B	B	B	A	B	B	A	A
Chrome Plating Solutions	D	D	B	B	D	D	D	B	A	A
Chromic Acid	D	D	C	C	D	C	B	C	A	A
Citric Acid	A	A	A	A	A	A	A	A	A	A

A - Recommended B - Minor to Moderate Effect C - Moderate to Severe Effect D - Not Recommended* Insufficient Data

Chemical	Natural Rubber, Isoprene (NR, IR)	Styrene, Butadiene (SBR, BR)	Butyl (IIR)	EPDM, EPM	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Silicone (SI, VMQ)	Viton, Fluoroelastomer (FKM)	Viton B Fluoroelastomer (FKM)
Coal Tar (Creosote)	D	D	D	D	A	B	D	D	A	A
Cobalt Chloride (Aqueous)	A	A	A	A	A	A	A	B	A	A
Cocanut Oil	D	D	C	C	A	B	C	A	A	A
Cod Liver Oil	D	D	A	A	A	B	B	B	A	A
Coke Oven Gas	D	D	D	D	D	D	C	B	A	A
Copper Acetate (Aqueous)	A	D	A	A	B	B	B	D	D	D
Copper Chloride (Aqueous)	A	A	A	A	A	B	B	A	A	A
Copper Cyanide (Aqueous)	A	A	A	A	A	A	A	A	A	A
Copper Sulfate (Aqueous)	B	B	B	A	A	A	A	A	A	A
Corn Oil	D	D	C	C	A	C	B	A	A	A
Cottonseed Oil	D	D	C	B	A	B	B	A	A	A
Creosote (Coal Tar)	D	D	D	D	A	B	D	D	A	A
Cresol	D	D	D	D	D	C	D	D	A	A
Cresylic Acid	D	D	D	D	D	C	D	D	A	A
Cumene	D	D	D	D	D	D	D	D	A	A
Cyclohexane	D	D	D	D	A	C	D	D	A	A
Cyclohexanol	D	D	D	C	C	A	B	D	A	A
Cyclohexanone	D	D	B	B	D	D	D	D	D	D

P-Cymene	D	D	D	D	D	D	D	D	A	A
A - Recommended B - Minor to Moderate Effect C - Moderate to Severe Effect D - Not Recommended* Insufficient Data										
Chemical	Natural Rubber, Isoprene (NR, IR)	Styrene, Butadiene (SBR, BR)	Butyl (IIR)	EPDM, EPM	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Silicone (SI, VMQ)	Viton, Fluoroelastomer (FKM)	Viton B Fluoroelastomer (FKM)
Decalin	D	D	D	D	D	D	D	D	A	A
Decane	D	D	D	D	A	D	C	B	A	A
Denatured Alcohol	A	A	A	A	A	A	A	A	A	A
Detergent Solutions	B	B	A	A	A	B	B	A	A	A
Developing Fluids	A	B	B	B	A	A	A	A	A	A
Diacetone	D	D	A	A	D	D	D	D	D	C
Diacetone Alcohol	D	D	A	A	D	B	B	B	D	C
Dibenzyl Ether	D	D	B	B	D	C	D	*	D	D
Dibenzyl Sebecate	D	D	B	B	D	D	D	C	B	A
Dibromoethylbenzene	D	D	D	D	D	D	D	D	B	A
Dibutyl Amine	D	D	D	C	D	D	D	C	D	D
Dibutyl Ether	D	D	C	C	D	C	D	D	C	C
Dibutyl Phthalate	D	D	C	B	D	D	D	B	C	A
Dibutyl Sebecate	D	D	B	B	D	D	D	B	B	A
O-Dichlorobenzene	D	D	D	D	D	D	D	D	A	A
Dichloro-Isopropyl Ether	D	D	D	C	D	D	D	D	C	C
Dicyclohexylamine	D	D	D	D	C	D	D		D	D
Diesel Oil	D	D	D	D	A	C	C	D	A	A
Diethylamine	B	B	B	B	B	B	C	B	D	D
Diethyl Benzene	D	D	D	D	D	D	D	D	A	A
Diethyl Ether	D	D	D	D	D	C	C	D	D	D
Diethylene Glycol	A	A	A	A	A	A	A	B	A	A
Diethyl Sebecate	D	D	B	B	B	D	B	B	B	A
Diisobutylene	D	D	D	D	B	D	D	D	A	A
Diisopropyl Benzene	D	D	D	D	D	D	D	*	A	A
Diisopropyl Ketone	D	D	A	A	D	D	D	D	D	D
Diisopropylidene Acetone (Phorone)	D	D	C	C	D	D	D	D	D	D
Dimethyl Aniline (Xylidine)	C	C	C	B	C	C	D	D	D	D
Dimethyl Ether (Methyl Ether)	D	D	D	D	A	C	C	A	D	D
Dimethyl Formamide	D	D	B	B	B	C	D	B	D	D
Dimethyl Phthalate	D	D	B	B	D	D	D	*	B	A
Dinitrotoluene	D	D	D	D	D	D	D	D	D	D
Diethyl Phtalate	D	D	B	B	C	D	D	C	B	A
Diethyl Sebecate	D	D	B	B	D	D	D	C	B	A
Dioxane	D	D	B	B	D	D	D	D	D	D
Dioxolane	D	D	C	B	D	D	D	D	D	D
Dipentene	D	D	D	D	B	D	D	D	A	A
Diphenyl (Biphenyl) (Phenylbenzene)	D	D	D	D	D	D	D	D	A	A
Diphenyl Oxides	D	D	D	D	D	D	D	C	A	A
Dowtherm Oil	D	D	D	D	D	D	D	C	A	A
Dry Cleaning Fluids	D	D	D	D	C	D	D	D	A	A
A - Recommended B - Minor to Moderate Effect C - Moderate to Severe Effect D - Not Recommended* Insufficient Data										
Chemical	Natural Rubber, Isoprene (NR, IR)	Styrene, Butadiene (SBR, BR)	Butyl (IIR)	EPDM, EPM	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Silicone (SI, VMQ)	Viton, Fluoroelastomer (FKM)	Viton B Fluoroelastomer (FKM)
Epichlorohydrin	D	D	B	B	D	D	D	D	D	D
Ethane	D	D	D	D	A	B	B	D	A	A
Ethanolamine	B	B	B	B	B	B	C	B	D	D
Ethyl Acetate	D	D	B	B	D	C	D	B	D	D
Ethyl Acetoacetate	C	C	B	B	D	C	D	B	D	D
Ethyl Acrylate	D	D	B	B	D	D	D	B	D	D
Ethyl Alcohol	A	A	A	A	A	A	A	A	B	A
Ethyl Benzene	D	D	D	D	D	D	D	D	A	A
Ethyl Benzoate	A	A	A	A	D	D	D	D	A	A

Ethyl Cellosolve	D	D	D	D	D	D	D	D	D	D
Ethyl Cellulose	B	B	B	B	B	B	B	C	D	D
Ethyl Chloride	D	D	D	C	A	D	D	D	A	A
Ethyl Chlorocarbonate	D	D	C	B	D	D	D	D	A	A
Ethyl Chloroformate	D	D	C	B	D	D	D	D	D	D
Ethyl Ether	D	D	C	C	C	C	D	D	D	D
Ethyl Formate	D	D	B	B	D	B	B	*	A	A
Ethyl Mercaptan	D	D	D	C	D	C	B	C	B	A
Ethyl Oxalate	A	A	A	A	D	C	D	D	A	A
Ethyl Pentachlorobenzene	D	D	D	D	D	D	D	D	A	A
Ethyl Silicate	B	B	A	A	A	A	B	*	A	A
Ethylene	C	C	B	B	A	C	*	*	A	A
Ethylene Chloride	D	D	C	C	D	D	D	D	B	A
Ethylene Chlorohydrin	B	B	B	B	D	B	B	C	A	A
Ethylene Diamine	A	B	A	A	A	A	B	A	D	D
Ethylene Dichloride	D	D	C	C	D	D	D	D	A	A
Ethylene Glycol	A	A	A	A	A	A	A	A	A	A
Ethylene Oxide	D	D	C	C	D	D	D	D	D	D
Ethylene Trichloride	D	D	C	C	D	D	D	D	A	A

A - Recommended B - Minor to Moderate Effect C - Moderate to Severe Effect D - Not Recommended* Insufficient Data

Chemical	Natural Rubber, Isoprene (NR, IR)	Styrene, Butadiene (SBR, BR)	Butyl (IIR)	EPDM, EPM	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Silicone (SI, VMQ)	Viton, Fluoroelastomer (FKM)	Viton B Fluoroelastomer (FKM)
Fatty Acids	D	D	C	C	B	B	B	C	A	A
Ferric Chloride (Aqueous)	A	A	A	A	A	A	A	B	A	A
Ferric Nitrate (Aqueous)	A	A	A	A	A	A	A	C	A	A
Ferric Sulfate (Aqueous)	A	A	A	A	A	A	A	B	A	A
Fish Oil	D	D	D	D	A	D	*	A	A	A
Fluorinated Cyclic Ethers	D	D	A	A	*	D	*	*	*	*
Fluorine (Liquid)	D	D	D	D	D	D	*	D	B	B
Fluorobenzene	D	D	D	D	D	D	*	D	A	A
Fluoroboric Acid	A	A	A	A	A	A	A	*	*	*
Fluorocarbon Oils	B	B	A	A		B	*	*	*	*
Fluorolube	B	C	A	A	A	B	A	A	B	A
Fluorosilicic Acid (Hydrofluosilicic Acid)	B	C	B	B	A	B	A	D	A	A
Formaldehyde (RT)	B	B	A	A	C	B	A	B	D	D
Formic Acid	B	A	A	A	B	A	A	B	C	D

A - Recommended B - Minor to Moderate Effect C - Moderate to Severe Effect D - Not Recommended* Insufficient Data

Chemical	Natural Rubber, Isoprene (NR, IR)	Styrene, Butadiene (SBR, BR)	Butyl (IIR)	EPDM, EPM	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Silicone (SI, VMQ)	Viton, Fluoroelastomer (FKM)	Viton B Fluoroelastomer (FKM)
Freon 11	D	D	D	D	B	C	A	D	A	A
Freon 12	B	A	B	B	A	A	A	D	B	A
Freon 13	A	A	A	A	A	A	A	D	A	A
Freon 21	D	D	D	D	D	D	D	D	D	D
Freon 22	B	A	A	A	D	A	A	D	D	D
Freon 31	B	B	A	A	D	B	B	*	D	D
Freon 32	A	A	A	A	A	A	A	*	D	D
Freon 112	D	C	D	D	B	C	B	D	A	A
Freon 113	C	B	D	C	A	A	A	D	B	A
Freon 114	A	A	A	A	A	A	A	D	B	A
Freon 115	A	A	A	A	A	A	A	*	B	A
Freon 142b	B	B	A	B	A	A	A	*	D	D
Freon 152b	A	A	A	A	A	A	C	*	D	D
Freon 218	A	A	A	A	A	A	A	*	A	A
Freon C316	A	A	A	A	A	A	A	*	B	A
Freon C318	A	A	A	A	A	A	A	*	B	A
Freon 13B1	A	A	A	A	A	A	A	D	A	A
Freon 114B2	D	C	D	D	B	C	A	D	B	A

Freon 502	A	A	A	A	B	A	*	*	B	A
Freon TF	D	C	D	D	A	A	A	D	B	A
Freon T-WD602	D	C	B	B	B	B	B	D	A	A
Freon TMC	D	D	C	C	B	C	B	C	A	A
Freon T-P35	A	A	A	A	A	A	A	A	A	A
Freon TA	C	C	B	B	A	B	A	C	D	C
Freon TC	D	C	B	B	A	A	A	D	A	A
Freon MF	D	D	D	D	A	C	B	D	B	A
Freon BF	D	D	D	D	B	C	B	D	A	A
Fuel Oil	D	D	D	D	A	B	B	D	A	A
Fumaric Acid	C	C	D	D	A	B	B	B	A	A
Furan, Furfuran	D	D	D	C	D	D	D	*	D	D
Furfural	D	D	B	B	D	C	C	D	D	D
Fyquel (Cellulube)	D	D	A	A	D	D	D	A	A	A

A - Recommended B - Minor to Moderate Effect C - Moderate to Severe Effect D - Not Recommended* Insufficient Data

Chemical	Natural Rubber, Isoprene (NR, IR)	Styrene, Butadiene (SBR, BR)	Butyl (IIR)	EPDM, EPM	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Silicone (SI, VMQ)	Viton, Fluoroelastomer (FKM)	Viton B Fluoroelastomer (FKM)
Gallic Acid	A	B	B	B	B	B	B	*	A	A
Gasoline	D	D	D	D	B	C	C	D	A	A
Gelatin	A	A	A	A	A	A	A	A	A	A
Glauber's Salt (Aqueous)	B	D	B	B	D	B	B	*	A	A
Glucose	A	A	A	A	A	A	A	A	A	A
Glue	B	B	B	A	A	A	A	A	A	A
Glycerin	A	A	A	A	A	A	A	A	A	A
Glycols	A	A	A	A	A	A	A	A	A	A
Green Sulfate Liquor	B	B	A	A	B	B	B	A	A	A

A - Recommended B - Minor to Moderate Effect C - Moderate to Severe Effect D - Not Recommended* Insufficient Data

Chemical	Natural Rubber, Isoprene (NR, IR)	Styrene, Butadiene (SBR, BR)	Butyl (IIR)	EPDM, EPM	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Silicone (SI, VMQ)	Viton, Fluoroelastomer (FKM)	Viton B Fluoroelastomer (FKM)
Halowax Oil	D	D	D	D	D	D	D	D	A	A
N-Hexaldehyde	D	D	B	A	D	A	C	B	D	D
Hexane	D	D	D	D	A	B	B	D	A	A
N-Hexene-1	D	D	D	D	B	B	B	D	A	A
Hexyl Alcohol	B	B	C	C	A	B	B	B	A	A
Hydrazine	A	A	A	A	B	B	B	C	D	D
Hydraulic Oil (Petroleum)	D	D	D	D	A	B	B	C	A	A
Hydrobromic Acid	A	D	A	A	D	D	A	D	A	A
Hydrobromic Acid 40%	A	D	A	A	D	B	A	D	A	A
Hydrochloric Acid (Cold) 37%	B	B	A	A	C	B	A	C	A	A
Hydrochloric Acid (Hot) 37%	D	D	C	C	D	D	D	D	B	A
Hydrocyanic Acid	B	B	A	A	B	B	A	C	A	A
Hydrofluoric Acid (Conc.) Cold	D	D	C	C	D	D	A	D	A	A
Hydrofluoric Acid (Conc.) Hot	D	D	D	D	D	D	C	D	D	D
Hydrofluoric Acid- Anhydrous	D	D	C	C	D	D	A	D	D	D
Hydrofluosilicic Acid (Fluosilicic Acid)	B	C	B	B	A	B	A	D	A	A
Hydrogen Gas	B	A	A	A	A	A	A	C	A	A
Hydrogen Peroxide (90%)	D	D	C	B	D	D	A	B	B	A
Hydrogen Sulfide (Wet) Cold	D	D	A	A	D	B	B	C	D	C
Hydrogen Sulfide (Wet) Hot	D	D	A	A	D	C	C	C	D	C
Hydroquinone	B	D	B	B	C	D	D	*	B	A
Hypochlorous Acid	B	D	B	B	D	D	D	*	A	A

A - Recommended B - Minor to Moderate Effect C - Moderate to Severe Effect D - Not Recommended* Insufficient Data

Chemical	Natural Rubber, Isoprene (NR, IR)	Styrene, Butadiene (SBR, BR)	Butyl (IIR)	EPDM, EPM	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Silicone (SI, VMQ)	Viton, Fluoroelastomer (FKM)	Viton B Fluoroelastomer (FKM)
Iodine Pentafluoride	D	D	D	D	D	D	D	D	D	D
Iodoform	D	D	D	D	*	D	*	*	C	B

Isobutyl Alcohol	A	B	A	A	B	A	A	A	A	A
Isooctane	D	D	D	D	A	B	B	D	A	A
Isophorone	D	D	C	C	D	D	D	D	D	D
Isopropyl Acetate	D	D	B	B	D	D	D	D	D	D
Isopropyl Alcohol	A	B	A	A	B	B	A	A	A	A
Isopropyl Chloride	D	D	D	D	D	D	D	D	A	A
Isopropyl Ether	D	D	D	D	B	C	C	D	D	D

A - Recommended B - Minor to Moderate Effect C - Moderate to Severe Effect D - Not Recommended* Insufficient Data

Chemical	Natural Rubber, Isoprene (NR, IR)	Styrene, Butadiene (SBR, BR)	Butyl (IIR)	EPDM, EPM	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Silicone (SI, VMQ)	Viton, Fluoroelastomer (FKM)	Viton B Fluoroelastomer (FKM)
Kerosene	D	D	D	D	A	B	C	D	A	A
Lacquers	D	D	D	D	D	D	D	D	D	B
Lacquer Solvents	D	D	D	D	D	D	D	D	D	D
Lactic Acid (Cold)	A	A	A	A	A	A	A	A	A	A
Lactic Acid (Hot)	D	D	D	D	D	D	C	B	A	A
Lard	D	D	B	B	A	B	D	B	A	A
Lavendar Oil	D	D	D	D	B	D	D	D	A	A
Lead Acetate (Aqueous)	A	D	A	A	B	B	D	D	D	D
Lead Nitrate (Aqueous)	A	A	A	A	A	A	A	B	A	A
Lead Sulfamate (Aqueous)	B	B	A	A	B	A	A	B	A	A
Ligroin (Benzine) (Nitrobenzine)	D	D	D	D	A	B	C	B	A	A
Lime Bleach	A	B	A	A	A	B	B	B	A	A
Lime Sulfur	D	D	A	A	D	A	A	A	A	A
Lindol (Hydraulic Fluid)	D	D	A	A	D	D	D	C	B	A
Linoleic Acid	D	D	D	D	B	D	D	B	B	A
Linseed Oil	D	D	C	C	A	B	B	A	A	A
Liquefied Petroleum Gas	D	D	D	D	A	B	B	C	A	A
Lubricating Oils (Petroleum)	D	D	D	D	A	B	B	D	A	A
Lye	B	B	A	A	B	B	A	B	B	A

A - Recommended B - Minor to Moderate Effect C - Moderate to Severe Effect D - Not Recommended* Insufficient Data

Chemical	Natural Rubber, Isoprene (NR, IR)	Styrene, Butadiene (SBR, BR)	Butyl (IIR)	EPDM, EPM	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Silicone (SI, VMQ)	Viton, Fluoroelastomer (FKM)	Viton B Fluoroelastomer (FKM)
Magnesium Chloride (Aqueous)	A	A	A	A	A	A	A	A	A	A
Magnesium Hydroxide (Aqueous)	B	B	A	A	B	A	A	*	A	A
Magnesium Sulfate (Aqueous)	B	B	A	A	A	A	A	A	A	A
Maleic Acid	C	C	B	B	D	C	D	*	A	A
Malic Acid	C	C	B	B	D	C	D	*	D	C
Mercury Chloride (Aqueous)	A	A	A	A	A	A	A	*	A	A
Mercury	A	A	A	A	A	A	A	*	A	A
Mesityl Oxide	D	D	B	B	D	D	D	D	D	D
Methane	D	D	D	D	A	B	B	D	A	A
Methyl Acetate	C	C	A	A	D	B	D	D	D	D
Methyl Acrylate	D	D	B	B	D	B	D	D	D	D
Methylacrylic Acid	D	D	B	B	D	B	D	D	D	D
Methyl Alcohol	A	A	A	A	A	A	A	A	D	A
Methyl Bromide	D	D	D	D	B	D	D	*	A	A
Methyl Butyl Ketone (Propyl Acetone)	D	D	A	A	D	D	D	C	D	D
Methyl Cellosolve	D	D	B	B	C	C	B	D	D	D
Methyl Chloride	D	D	C	C	D	D	D	D	B	A
Methyl Cyclopentane	D	D	D	D	D	D	D	D	A	A
Methylene Chloride	D	D	D	C	D	D	D	D	B	B
Methyl Ether (Dimethyl Ether)	D	D	D	D	A	C	C	A	D	D
Methyl Ethyl Ketone	D	D	B	A	D	C	D	D	D	D
Methyl Formate	D	D	B	B	D	B	B	*	D	D
Methyl Isobutyl Ketone	D	D	C	B	D	D	D	D	D	D
Methyl Methacrylate	D	D	D	C	D	D	D	D	D	D
Methyl Oleate	D	D	B	B	D	D	D	*	B	A

Methyl Salicylate	C	C	B	B	D	D	D	*	B	A
Milk	A	A	A	A	A	A	A	A	A	A
Mineral Oil	D	D	C	C	A	B	B	B	A	A
Monochlorobenzene	D	D	D	D	D	D	D	D	A	A
Monomethyl Aniline	D	D	B	B	D	D	D	*	B	B
Monoethanol Amine	B	B	B	A	D	D	D	B	D	D
Monomethyl Ether (Methyl Ether)	D	D	D	D	A	C	B	A	D	D
Monovinyl Acetylene	B	B	B	B	A	B	B	B	A	A
Mustard Gas	A	B	A	A	*	A	A	A	A	A

A - Recommended B - Minor to Moderate Effect C - Moderate to Severe Effect D - Not Recommended* Insufficient Data

Chemical	Natural Rubber, Isoprene (NR, IR)	Styrene, Butadiene (SBR, BR)	Butyl (IIR)	EPDM, EPM	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Silicone (SI, VMQ)	Viton, Fluoroelastomer (FKM)	Viton B Fluoroelastomer (FKM)
Naphtha	D	D	D	D	B	C	D	D	A	A
Naphthalene	D	D	D	D	D	D	D	D	A	A
Naphthalenic Acid	D	D	D	D	B	D	D	D	A	A
Natural Gas	B	B	D	D	A	A	A	A	A	A
Neats Foot Oil	D	D	B	B	A	D	D	B	A	A
Neville Acid	D	D	B	B	D	D	D	D	A	A
Nickel Acetate (Aqueous)	A	D	A	A	B	B	D	D	D	D
Nickel Chloride (Aqueous)	A	A	A	A	A	A	A	A	A	A
Nickel Sulfate (Aqueous)	B	B	A	A	A	A	A	A	A	A
Niter Cake	A	A	A	A	A	A	A	A	A	A
Nitric Acid (Conc.)	D	D	D	D	D	D	B	D	B	A
Nitric Acid (Dilute)	D	D	B	B	D	B	A	B	A	A
Nitric Acid-Red Fuming	D	D	D	D	D	D	D	D	C	B
Nitrobenzene	D	D	A	A	D	D	D	D	B	A
Nitrobenzene (Petroleum Ether)	D	D	D	D	A	B	C	D	A	A
Nitroethane	B	B	B	B	D	C	B	D	D	D
Nitrogen	A	A	A	A	A	A	A	A	A	A
Nitrogen Tetroxide	D	D	C	C	D	D	D	D	D	D
Nitromethane	B	B	B	B	D	B	C	D	D	D

A - Recommended B - Minor to Moderate Effect C - Moderate to Severe Effect D - Not Recommended* Insufficient Data

Chemical	Natural Rubber, Isoprene (NR, IR)	Styrene, Butadiene (SBR, BR)	Butyl (IIR)	EPDM, EPM	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Silicone (SI, VMQ)	Viton, Fluoroelastomer (FKM)	Viton B Fluoroelastomer (FKM)
Octachlorotoluene	D	D	D	D	D	D	D	D	A	A
Octadecane	D	D	D	D	A	B	B	D	A	A
N-Octane	D	D	D	D	B	B	B	D	A	A
Octyl Alcohol	B	B	C	C	B	A	B	B	A	A
Oleic Acid	D	D	D	D	C	C	C	D	B	B
Oleum Spirits	D	D	D	D	B	C	B	D	A	A
Olive Oil	D	D	B	B	A	B	B	C	A	A
O-Dichlorobenzene	D	D	D	D	D	D	D	D	A	A
Oxalic Acid	B	B	A	A	B	B	B	B	A	A
Oxygen-Cold	B	B	A	A	B	A	A	A	A	A
Oxygen-(200-400oF)	D	D	D	C	D	D	D	B	B	A
Ozone	D	D	B	A	D	C	A	A	A	A

A - Recommended B - Minor to Moderate Effect C - Moderate to Severe Effect D - Not Recommended* Insufficient Data

Chemical	Natural Rubber, Isoprene (NR, IR)	Styrene, Butadiene (SBR, BR)	Butyl (IIR)	EPDM, EPM	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Silicone (SI, VMQ)	Viton, Fluoroelastomer (FKM)	Viton B Fluoroelastomer (FKM)
Paint Thinner, Duco	D	D	D	D	D	D	D	D	B	A
Palmitic Acid	B	B	B	B	A	B	C	D	A	A
Peanut Oil	D	D	C	C	A	C	B	A	A	A
Perchloric Acid	D	D	B	B	D	B	B	D	A	A
Perchloroethylene	D	D	D	D	B	D	D	D	A	A
Petroleum-Below 250oF	D	D	D	D	A	B	B	B	A	A
Petroleum-Above 250oF	D	D	D	D	D	B	D	D	B	A

Phenol (Carbolic Acid)	D	*	B	B	D	C	D	D	A	A
Phenylbenzene (Biphenyl) (Diphenyl)	D	D	D	D	D	D	D	D	A	A
Phenyl Ethyl Ether	D	D	D	D	D	D	D	D	D	D
Phenyl Hydrazine	A	B	B	B	D	D	D	*	B	A
Phorone (Diisopropylidene Acetone)	D	D	C	C	D	D	D	D	D	D
Phosphoric Acid-20%	B	B	B	A	B	B	A	B	A	A
Phosphoric Acid-45%	C	C	B	A	D	B	B	C	A	A
Phosphorus Trichloride	D	D	A	A	D	D	D	*	A	A
Pickling Solution	D	D	C	C	D	D	B	D	A	A
Picric Acid	B	B	B	B	B	A	B	D	A	A
Pinene	D	D	D	D	B	C	C	D	A	A
Pine Oil	D	D	D	D	D	D	D	D	A	A
Piperidine	D	D	D	D	D	D	D	D	D	D

A - Recommended B - Minor to Moderate Effect C - Moderate to Severe Effect D - Not Recommended* Insufficient Data

Chemical	Natural Rubber, Isoprene (NR, IR)	Styrene, Butadiene (SBR, BR)	Butyl (IIR)	EPDM, EPM	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Silicone (SI, VMQ)	Viton, Fluoroelastomer (FKM)	Viton B Fluoroelastomer (FKM)
Plating Solution- Chrome	D	D	A	A	*	D	D	D	A	A
Plating Solution- Others	D	D	A	A	A	D	A	D	A	A
Polyvinyl Acetate Emulsion	B	D	A	A	*	B	B	*	*	*
Potassium Acetate (Aqueous)	A	D	A	A	B	B	A	D	D	D
Potassium Chloride (Aqueous)	A	A	A	A	A	A	A	A	A	A
Potassium Cupro Cyanide	A	A	A	A	A	A	A	A	A	A
Potassium Cyanide (Aqueous)	A	A	A	A	A	A	A	A	A	A
Potassium Dichromate (Aqueous)	B	B	A	A	A	A	A	A	A	A
Potassium Hydroxide (Aqueous)	B	B	A	A	A	A	A	A	A	A
Potassium Nitrate (Aqueous)	A	A	A	A	A	A	A	A	A	A
Potassium Sulfate (Aqueous)	B	A	A	A	A	A	A	A	A	A
Producer Gas	D	D	D	D	A	B	B	B	A	A
Propane	D	D	D	D	A	B	B	D	A	A
i-Propyl Acetate	D	D	B	B	D	D	D	D	D	D
n-Propyl Acetate	D	D	B	B	D	D	D	D	D	D
Propyl Acetone (Methyl Butyl Ketone)	D	D	A	A	D	D	D	C	D	D
Propyl Alcohol	A	A	A	A	A	A	A	A	A	A
Propyl Nitrate	D	D	B	B	D	D	D	D	D	D
Propylene	D	D	D	D	D	D	D	D	A	A
Propylene Oxide	D	D	B	B	D	D	D	D	D	D
Pydraul, 10E, 29 ELT	D	D	A	A	D	D	D	D	A	A
Pydraul, 30E, 50E, 65E, 90E	D	D	A	A	D	D	D	A	A	A
Pydraul, 115E	D	D	A	A	D	D	D	D	A	A
Pydraul, 230E, 312C, 540C	D	D	D	D	D	D	D	D	A	A
Pyranol, Transformer Oil	D	D	D	D	A	B	C	D	A	A
Pyridine	D	D	B	B	D	D	D	D	D	D
Pyroligneous Acid	D	D	B	B	D	B	B	*	D	D
Pyrrrole	C	C	D	C	D	D	D	B	D	D

A - Recommended B - Minor to Moderate Effect C - Moderate to Severe Effect D - Not Recommended* Insufficient Data

Chemical	Natural Rubber, Isoprene (NR, IR)	Styrene, Butadiene (SBR, BR)	Butyl (IIR)	EPDM, EPM	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Silicone (SI, VMQ)	Viton, Fluoroelastomer (FKM)	Viton B Fluoroelastomer (FKM)
Radiation	C	C	D	B	C	B	C	C	C	C
Rapeseed Oil	D	D	A	A	B	B	B	D	A	A
Red Oil (MIL-H-5606)	D	D	D	D	A	B	B	D	A	A
RJ-1 (MIL-F-25558 B)	D	D	D	D	A	B	B	D	A	A
RP-1 (MIL-F-25576 C)	D	D	D	D	A	B	B	D	A	A
Sal Ammoniac	A	A	A	A	A	A	A	B	A	A
Salicylic Acid	A	B	A	A	B	A	*	*	A	A
Salt Water	A	A	A	A	A	B	A	A	A	A
Sewage	B	B	B	B	A	B	A	B	A	A
Silicate Esters	D	D	D	D	B	A	A	D	A	A

Silicone Greases	A	A	A	A	A	A	A	C	A	A
Silicone Oils	A	A	A	A	A	A	A	C	A	A
Silver Nitrate	A	A	A	A	B	A	A	A	A	A
Skydrol 500	D	D	B	A	D	D	D	C	D	D
Skydrol 7000	D	D	A	A	D	D	D	C	B	A
A - Recommended B - Minor to Moderate Effect C - Moderate to Severe Effect D - Not Recommended* Insufficient Data										
Chemical	Natural Rubber, Isoprene (NR, IR)	Styrene, Butadiene (SBR, BR)	Butyl (IIR)	EPDM, EPM	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Silicone (SI, VMQ)	Viton, Fluoroelastomer (FKM)	Viton B Fluoroelastomer (FKM)
Soap Solutions	B	A	A	A	A	B	A	A	A	A
Soda Ash	A	A	A	A	A	A	A	A	A	A
Sodium Acetate (Aqueous)	A	D	A	A	B	B	A	D	D	D
Sodium Bicarbonate (Aqueous)(Baking Soda)	A	A	A	A	A	A	A	A	A	A
Sodium Bisulfite (Aqueous)	A	B	A	A	A	A	A	A	A	A
Sodium Borate (Aqueous)	A	A	A	A	A	A	A	A	A	A
Sodium Chloride (Aqueous)	A	A	A	A	A	A	A	A	A	A
Sodium Cyanide (Aqueous)	A	A	A	A	A	A	A	A	A	A
Sodium Hydroxide (Aqueous)	A	A	A	A	B	A	A	B	B	A
Sodium Hypochlorite (Aqueous) (Chlorox)	D	D	B	B	B	A	A	B	A	A
Sodium Metaphosphate (Aqueous)	A	A	A	A	A	B	B	*	A	A
Sodium Nitrate (Aqueous)	B	A	A	A	B	B	A	D	A	A
Sodium Perborate (Aqueous)	B	B	A	A	B	B	B	B	A	A
Sodium Peroxide (Aqueous)	B	B	A	A	B	B	B	D	B	A
Sodium Phosphate (Aqueous)	A	A	A	A	A	B	A	D	A	A
Sodium Silicate (Aqueous)	A	A	A	A	A	A	A	*	A	A
Sodium Sulfate (Aqueous)	B	B	A	A	A	A	A	A	A	A
Sodium Thiosulfate (Aqueous)	B	B	A	A	B	A	A	A	A	A
Soybean Oil	D	D	C	C	A	B	C	A	A	A
Stannic Chloride (Aqueous)	A	A	A	A	A	B	A	B	A	A
Stannous Chloride (Aqueous)	A	A	A	A	A	A	A	B	A	A
Steam Under 300oF	D	D	B	A	D	C	D	C	D	B
Steam Over 300oF	D	D	D	C	D	D	D	D	D	D
Stearic Acid	B	B	B	B	B	B	B	B	A	A
Stoddard Solvent	D	D	D	D	A	B	D	D	A	A
Styrene	D	D	D	D	D	D	D	D	B	A
A - Recommended B - Minor to Moderate Effect C - Moderate to Severe Effect D - Not Recommended* Insufficient Data										
Chemical	Natural Rubber, Isoprene (NR, IR)	Styrene, Butadiene (SBR, BR)	Butyl (IIR)	EPDM, EPM	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Silicone (SI, VMQ)	Viton, Fluoroelastomer (FKM)	Viton B Fluoroelastomer (FKM)
Sucrose Solution	A	A	A	A	A	B	B	A	A	A
Sulfite Liquors	B	B	B	B	B	B	B	D	A	A
Sulfur	D	D	A	A	D	A	A	C	A	A
Sulfur Chloride (Aqueous)	D	D	D	D	C	C	B	C	A	A
Sulfur Dioxide (Dry)	B	B	B	A	D	D	B	B	B	A
Sulfur Dioxide (Wet)	D	D	A	A	D	B	A	B	B	A
Sulfur Dioxide (Liquified Under Pressure)	D	D	B	A	D	D	D	B	B	A
Sulfur Hexafluoride	D	D	A	A	B	A	B	B	A	A
Sulfur Trioxide	B	B	B	B	D	D	D	B	A	A
Sulfuric Acid (Dilute)	C	C	B	B	C	B	A	D	A	A
Sulfuric Acid (conc.)	D	D	D	C	D	D	A	D	A	A
Sulfuric Acid (20% Oleum)	D	D	D	D	D	D	D	D	A	A
Sulfurous Acid	B	B	B	B	B	B	A	D	C	B
A - Recommended B - Minor to Moderate Effect C - Moderate to Severe Effect D - Not Recommended* Insufficient Data										
Chemical	Natural Rubber, Isoprene (NR, IR)	Styrene, Butadiene (SBR, BR)	Butyl (IIR)	EPDM, EPM	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Silicone (SI, VMQ)	Viton, Fluoroelastomer (FKM)	Viton B Fluoroelastomer (FKM)
Tannic Acid	A	B	A	A	A	A	A	B	A	A
Tar, Bituminous	D	D	C	C	B	C	D	B	A	A
Tartaric Acid	C	D	B	B	A	B	A	A	A	A

